

INSTRUCTIONS

ACRYLIC POLYURETHANE WATERPROOF COATING AQUACOATZ™

VOLUME

1 kg

ABOUT THE ITEM

YF-200 polyurethane anti-corrosion and waterproof coating is a single-component polyurethane coating composed of polyurethane prepolymers, functional additives, and fillers. When applied to the surface, the product reacts with the moisture in the air to form a dense, elastic, high-performance rubber coating.

- Ready to use, convenient for construction.
- Eco-friendly, waterproof and anti-corrosive.
- Strong adhesive force, high wear resistance.
- Super strong crack resistance, good water resistance.



SCOPE OF APPLICATION

- Waterproofing projects for various types of roofs and bathrooms.
- Waterproofing on the water-facing surfaces of underground structural elements.
- Waterproofing and anti-corrosion for water-facing surfaces of sewage treatment tanks, basements, swimming pools, civil defense projects, storage tanks, culverts, tunnels, bridges, reservoirs, etc.
- Corrosion protection for metal pipelines, workshop floors, water tanks, etc. and bonding of wooden floors, cement boards, asbestos products, fiberglass products, ceramic products, floor tiles, and more.
- Can also be used as a sealing material for building structures.

HOW TO USE

- **CONSTRUCTION METHOD:** Apply directly to the surface using a roller, brush or spray machine.
- **STORAGE CONDITIONS:** Store the product in a sealed container in a cool, dry place above 0°C, away from heat and direct sunlight.
- **SURFACE PREPARATION:** The surface must be smooth, solid, clean, free of oil stains, dust, and other loose materials. Obvious gaps and pinholes should be filled and smoothed with cement mortar, and sharp edges should be removed. For sandy surfaces, our company's sand fixing agent should be used for wall reinforcement treatment before proceeding with waterproofing construction.

- **PRECAUTIONS:** Do not apply below 0°C or during rain. The mixed paste should be used within 2 hours. In areas with high humidity and poor ventilation, ventilation equipment should be used to accelerate the curing of the waterproof layer.
- **RECOMMENDED USAGE:** The amount of waterproof material required for two coats applied directly by brushing is approximately 1–2 kg/m², with a thickness of about 1–1.2 mm. For areas with severe water permeability, multiple layers can be applied to achieve the thickness required by relevant waterproofing engineering technical specifications.

WARNINGS

- For external use only.
- Keep out of reach of children.
- Avoid contact with eyes.
- Discontinue use if signs of irritation or rash occur.
- Store in a cool and dry place.
- Do not eat, drink, or smoke when using this product.
- Wear eye/face protection.
- Ingredients: acrylic polymer, water, water-based color paste, calcium powder, fungicide, defoamer.
- Dispose of contents/container in accordance with national regulations.
- Shelf life: 12 months.
- Made in China.

